



Figure S1. Cyclic voltammograms resulting from increasing scan rate (10–200 mV s^{-1}) and plot peak current versus square root of the scan rate at DCell (A,B) and DCell modified with $\text{Ag}/\delta\text{-FeOOH}$ (C,D) and DCell modified with $\text{CB}/\text{Ag}/\delta\text{-FeOOH}$ (E,F) in 1 mM of $\text{K}_3\text{Fe}(\text{CN})_6$ and 1 mM of $\text{K}_4\text{Fe}(\text{CN})_6$ in 0.1 M KCl pH 3.2.

Table S1. LOD values for other modified electrodes for H₂O₂ detection

Sample	LOD	Reference
Ag/ δ -FeOOH	71 μ M	[1]
CFP/ α -FeOOH	18 μ M	[2]
PPy/CB/ α -Fe ₂ O ₃	52.8 nM	[3]
Fe ₃ O ₄ – BCAMW	503 μ M	[4]
Fe ₃ O ₄ /Gr/CC	4.79 μ M	[5]
CB//Ag/ δ -FeOOH	21.6 μ M	(This work)

LOD = detection limit; LOQ = quantification limit.

References

1. de Meira, F.H.A.; Resende, S.F.; Monteiro, D.S.; Pereira, M.C.; Mattoso, L.H.C.; Faria, R.C.; Afonso, A.S. A Non-enzymatic Ag/ δ -FeOOH Sensor for Hydrogen Peroxide Determination using Disposable Carbon-based Electrochemical Cells. *Electroanalysis* **2020**, *32*, 2231–2236, doi:10.1002/elan.202060171.
2. Du, S.C.; Ren, Z.Y.; Wu, J.; Xi, W.; Fu, H.G. Vertical α -FeOOH nanowires grown on the carbon fiber paper as a free-standing electrode for sensitive H₂O₂ detection. *Nano Res.* **2016**, *9*, 2260–2269, doi:10.1007/s12274-016-1113-y.
3. Ahmed, J.; Faisal, M.; Jalalah, M.; Alsaiari, M.; Alsareii, S.A.; Harraz, F.A. An efficient amperometric catechol sensor based on novel polypyrrole-carbon black doped α -Fe₂O₃ nanocomposite. *Colloid Surf. A-Physicochem. Eng. Asp.* **2021**, *619*, 12, doi:10.1016/j.colsurfa.2021.126469.
4. Ates, A.; Oskay, K.O. Preparation and characterization of nanosized Fe₃O₄-biochar electrocatalysts with large surface area for H₂O₂ sensing. *Surf. Interfaces* **2022**, *29*, 14, doi:10.1016/j.surfin.2022.101733.
5. Sobahi, N.; Imran, M.; Khan, M.E.; Mohammad, A.; Alam, M.M.; Yoon, T.; Mehedi, I.M.; Hussain, M.A.; Abdulaal, M.J.; Jiman, A.A. Electrochemical Sensing of H₂O₂ by Employing a Flexible Fe₃O₄/Graphene/Carbon Cloth as Working Electrode. *Materials* **2023**, *16*, 18, doi:10.3390/ma16072770.