

Supplementary Information




Figure S1. Time dependence SnO_x deposition. AFM images of SnO_x deposition on glass at different times following the initiation of deposition. Red labels give the time after deposition began: 5, 30, 60, 300, 1200, 3600, 7200, 10,800 s. SnCl_2 concentration is 27 mM. Vertical and horizontal scales in these AFM images are 15 nm/div and 200nm/div respectively.