

Characterization of Solvent-Treated PEDOT:PSS Thin Films with Enhanced Conductivities

Syang-Peng Rwei ^{1,2,*}, Yi-Huan Lee ^{1,2}, Jia-Wei Shiu ^{1,2}, Ragu Sasikumar ² and Uin-Ting Shyr ^{1,2}

¹ Institute of Organic and Polymeric Materials, National Taipei University of Technology, Taipei 10608, Taiwan (R.O.C); yihuanlee@mail.ntut.edu.tw (Y.-H.L.); hahaluckybowen@gmail.com (J.-W.S.); alexilaiho0422@gmail.com (U.-T.S.)

² Research and Development Center for Smart Textile Technology, National Taipei University of Technology, Taipei 10608, Taiwan (R.O.C); sasi.che2011@gmail.com

* Correspondence: f10714@ntut.edu.tw

Table S1. Conductivities of the untreated PEDOT:PSS thin film A (2.4% PSSAS), B (4.8% PSSAS) and C (6.2% PSSAS) with an thermal annealing under air atmosphere at 140 °C for 5 min.

Processes	Films	Conductivity for each sample (S/cm)	
			Average conductivity (S/cm)
Thermal annealing (110 °C, 30 min)	Film A	0.18	0.19
+ without solvent treating	Film B	0.21 0.52 0.54 0.53	0.53
+ thermal annealing (140 °C, 5 min)	Film C	0.34 0.31 0.29	0.31