



Figure S1 Morphology of ablated surface.

Figure S1 presents Laser-induced periodic surface ripples formed through femtosecond ablation on HEA target surface. Periodicity of  $\sim 200$  nm observed, in line with laser wavelength expected to induce such self-organized structures.