

Supplementary Material




Figure S1. AFM tapping mode images of: (a) PS, (b) PS+F127, (c) PS+PLL-g-PEG, (d) PS+DOPA, (e) PS+DOPA+F127, (f) PS+DOPA+PLL-g-PEG. All images are 1 μm wide.

Table S1. Roughness recorded for one sample of each surface.

Surface	RMS Roughness (nm) from 5 μm Image
PS	0.32
PS+F127	1.03
PS+PLL-g-PEG	0.98
PS+DOPA	0.97
PS+DOPA+F127	6.39
PS+DOPA+PLL-g-PEG	2.27