

Atomic %	C	O	Na	Mg	Si	P	K	Ca	Cl	Al
Trial a	36.31	40.54	1.25	4.88	1.98	10.30	0.53	4.22	-	-
Trial b	36.40	37.36	0.89	5.13	4.13	11.21	0.70	4.18	-	0.01
Trial c	32.34	40.74	2.35	5.45	1.87	11.47	0.42	5.13	0.23	-
Mean	35.02	39.55	1.50	5.15	2.66	10.99	0.55	4.51	Not considered	Not considered
Standard Deviation	2.32	1.90	0.76	0.29	1.27	0.61	0.14	0.54	Not considered	Not considered

Table S1: Percentage composition of B-MP obtained through EDX analysis.