

Supplementary Materials: Magnetic properties and microstructure of FeCoNi(CuAl)_{0.8}Sn_x (0 ≤ x ≤ 0.10) High-Entropy Alloys

Zhong Li ¹, Chenxu Wang ¹, Linye Yu ^{1,2}, Yong Gu ^{1,3}, Minxiang Pan ¹, Xiaohua Tan^{1,*} and Hui Xu^{1,*}




Figure S1. DSC curves of FeCoNi(CuAl)_{0.8}Sn_x (0 ≤ x ≤ 0.10) HEAs

Table S1 The melting points (K) [28] of different elements and the mixing enthalpies (kJ/mol) [29]

Element	T _m / K	between two elements					
		Fe	Co	Ni	Cu	Al	
Fe	1808	-	-	-	-	-	-
Co	1767	-1	-	-	-	-	-
Ni	1726	-2	0	-	-	-	-
Cu	1358	13	6	4	-	-	-
Al	933	-11	-19	-22	-1	-	-
Sn	505	11	0	-4	7	4	