



Figure S1. SEM images of CC-1000(a), CC-1200(b), CC-1400(c), CC-1600(d).

Table S1. The percent of C, O atoms and functionalities calculated by XPS.

| | C atoms(%) | O atoms(%) | C=C(%) | C-C(%) | C-O(%) | C=O(%) |
|---------|-------------------|-------------------|---------------|---------------|---------------|---------------|
| CC-1000 | 92.37 | 7.20 | 25.80 | 44.56 | 13.05 | 8.96 |
| CC-1200 | 93.94 | 5.96 | 27.61 | 44.04 | 13.94 | 8.85 |
| CC-1400 | 95.45 | 2.87 | 29.91 | 42.32 | 15.98 | 7.24 |
| CC-1600 | 94.89 | 5.02 | 26.65 | 48.30 | 15.57 | 4.37 |