

Supplementary Materials

Novel Aggregation-Induced Emission Materials/Cadmium Sulfide Composite Photocatalyst for Efficient Hydrogen Evolution in Absence of Sacrificial Reagent

Xi Ke¹, Kunqiang Wang¹, Chen Tu², Runda Huang³, Dongxiang Luo^{1,*} and Menglong Zhang^{1,*}

¹ Institute of Semiconductors, South China Normal University, Guangzhou 510631, China; xike@m.scnu.edu.cn (X.K.); kunqiangwang@m.scnu.edu.cn (K.W.)

² School of Chemistry, Faculty of Science, Chemistry Building F11, Camperdown 2050, University of Sydney, Camperdown NSW 2006, Australia; chtu4116@uni.sydney.edu.au

³ School of Materials and Energy, Guangdong University of Technology, Guangzhou 510006, China; hrzd6287211@163.com

* Correspondence: luodx@gdut.edu.cn (D.L.); mlzhang@m.scnu.edu.cn (M.Z.)

DFT Calculation of Band Structure of TEP-Ca




Figure S1. Frontier molecular orbital distributions and energy level diagram of TPE-Ca obtained by DFT calculations (B3LYP/6-31G*).

X-Ray Single-Crystal Diffraction of TEP-Ca

Table S1. The main parameters of TEP-Ca.

Parameter	TPE-Ca
Empirical formula	C ₅₃ H ₃₆ N ₂
Formula weight[g mol ⁻¹]	700.84
Crystal system	monoclinic
Space group	P 1 21/n 1
A [Å]	19.8975(12)
B [Å]	9.0425(6)
C [Å]	21.1651(13)
α [°]	-
β[°]	92.499(2)
γ[°]	--
Volume [Å ³]	3804.5(4)
Z	4
Density, calcd [g m ⁻³]	1.224
Temperature [K]	220
Unique reflns	6845
Obsdreflns	7994
Parameters	496
R _{int}	0.0636
R[I > 2σ(I)] ^a	0.1698
wR[I > 2σ(I)]I ^b	0.1830
GOF on F ²	1.024



© 2020 by the authors. Submitted for possible open access publication under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).