

Composites of Laminar nanostructured ZnO and VOx-Nanotubes Hybrid as Visible Light Active Photocatalysts

Eglantina Benavente^{1*}, Daniel Navas¹, Sindy Devis¹, Marjorie Segovia², Clivia Sotomayor-Torres^{3,4} and Guillermo González^{2,5}




Figure S1. Experimental system of the beaker with 25 ml of MB under solar simulated light

Table S1. Diffraction data and distances corresponding to (001) reflections

Sample	2 θ	Distance (001) (nm)
ZnO (stearic acid)	1,70	4,85 nm
VOx-NTs	2,58	2,90 nm