



Article Ultrathin Leaf-Shaped CuO Nanosheets Based Sensor Device for Enhanced Hydrogen Sulfide Gas Sensing Application

Ahmad Umar ^{1,2,*}, Hassan Algadi ^{1,3}, Rajesh Kumar ⁴, Mohammad Shaheer Akhtar ^{5,*}, Ahmed A. Ibrahim ^{1,2}, Hasan Albargi ^{1,6}, Mohsen A. M. Alhamami ², Turki Alsuwian ³ and Wen Zeng ⁷

- ¹ Promising Centre for Sensors and Electronic Devices (PCSED), Najran University, Najran 11001, Saudi Arabia; hassan.algadi@gmail.com (H.A.); ahmedragal@yahoo.com (A.A.I.); albargih@yahoo.com (H.A.)
- ² Department of Chemistry, Faculty of Science and Arts, Najran University, Najran 11001, Saudi Arabia; maalhammami@nu.edu.sa
- ³ Department of Electrical Engineering, College of Engineering, Najran University, Najran 11001, Saudi Arabia; tmalsuwian@nu.edu.sa
- ⁴ Department of Chemistry, Jagdish Chandra DAV College Dasuya, Punjab 144205, India; rk.ash2k7@gmail.com
- ⁵ New & Renewable Energy Material Development Center (NewREC), Jeonbuk National University, Jeonbuk 56332, Korea
- Department of Physics, Faculty of Science and Arts, Najran University, Najran 11001, Saudi Arabia
- College of Materials Science and Engineering, Chongqing University, Chongqing 400044, China; wenzeng@cqu.edu.cn
- * Correspondence: ahmadumar786@gmail.com or umahmad@nu.edu.sa (A.U.); shaheerakhtar@jbnu.ac.kr (M.S.A.)

Abstract: Herein, a simple, economical and low temperature synthesis of leaf-shaped CuO nanosheets is reported. As-synthesized CuO was examined through different techniques including field emission scanning electron microscopy (FESEM), energy dispersive spectroscopy (EDS), transmission electron microscopy (TEM), high-resolution TEM (HRTEM), X-ray diffraction (XRD), fourier transform infrared spectroscopic (FTIR) and Raman spectroscopy to ascertain the purity, crystal phase, morphology, vibrational, optical and diffraction features. FESEM and TEM images revealed a thin leaf-like morphology for CuO nanosheets. An interplanar distance of ~0.25 nm corresponding to the (110) diffraction plane of the monoclinic phase of the CuO was revealed from the HRTEM images XRD analysis indicated a monoclinic tenorite crystalline phase of the synthesized CuO nanosheets. The average crystallite size for leaf-shaped CuO nanosheets was found to be 14.28 nm. Furthermore, a chemo-resistive-type gas sensor based on leaf-shaped CuO nanosheets was fabricated to effectively and selectively detect H₂S gas. The fabricated sensor showed maximum gas response at an optimized temperature of 300 $^{\circ}$ C towards 200 ppm H₂S gas. The corresponding response and recovery times were 97 s and 100 s, respectively. The leaf-shaped CuO nanosheets-based gas sensor also exhibited excellent selectivity towards H_2S gas as compared to other analyte gases including NH_3 , CH_3OH , CH₃CH₂OH, CO and H₂. Finally, we have proposed a gas sensing mechanism based upon the formation of chemo-resistive CuO nanosheets.

Keywords: leaf-shaped; nanosheets; CuO; gas sensor; H₂S

1. Introduction

Recently, detecting hazardous substances and continuously monitoring the air pollutants, toxic gases and volatile organic gases have become the key to create a safe and healthy environment for society. Vehicular and other industrial activities are adding a variety of harmful toxic gases tremendously to the environment daily. Continuous exposure to such gases is the cause of serious health related problems in humans [1,2]. One such harmful gas is hydrogen sulfide (H₂S) which is highly corrosive, inflammable, and explosive, thus an extremely hazardous gas. Exposure to low concentrations of H₂S gas may cause a sore throat, coughing, skin itching, eye irritation and inflammation and irritation in the respiratory track, etc. [3,4]. In contrast, exposure to high concentrations (>100 ppm) may lead



Citation: Umar, A.; Algadi, H.; Kumar, R.; Akhtar, M.S.; Ibrahim, A.A.; Albargi, H.; Alhamami, M.A.M.; Alsuwian, T.; Zeng, W. Ultrathin Leaf-Shaped CuO Nanosheets Based Sensor Device for Enhanced Hydrogen Sulfide Gas Sensing Application. *Chemosensors* 2021, *9*, 221. https://doi.org/10.3390/ chemosensors9080221

Academic Editors: Shaolin Zhang and Fang Xu

Received: 7 July 2021 Accepted: 5 August 2021 Published: 11 August 2021

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Copyright: © 2021 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (https:// creativecommons.org/licenses/by/ 4.0/). to olfactory nerve paralysis, loss of consciousness, myocardial damage and Alzheimer's disease. H₂S exposure above 300 ppm may cause the sudden collapse of the cardiovascular system, damage to the human lungs and central nervous system [5–7].

A plethora of different analytical methods including conductometric [8], spectroscopic [9], micro-cantilever [10], gas chromatography [11], surface plasmon resonance [12], surface acoustic [13], field-emission transistors [14], microwave, [15] and chemo-resistive sensors based on nano-sized semiconductor metal oxides that have emerged as potential gas sensor materials and have been exhaustively investigated for variety of hazardous toxic gases [16,17]. Recently, many metals oxide-based gas sensors based on a chemo-resistive technique have been reported for H₂S gas sensing and monitoring. Qiao et al. [18] reported Mo-doped BiVO₄ were with high sensitivity, selectivity, fast response towards 20 ppm H₂S at optimized temperature of 150 °C. Li et al. [19] analyzed the effect of integrating p-type and n-type semiconductor for H_2S by synthesizing metal-organic frameworksderived bamboo-like CuO/In₂O₃ heterostructure. Flower-like structures composed of vertical aligned ZnO nanorods showed a high response and selectivity for H₂S at room temperature [20]. Hydrothermally synthesized pure ZnO and Cu-doped ZnO nanostructures decorated with reduced graphene oxide were compared for their H_2S gas sensing behavior by Shewale et al. [21] and it was concluded that Cu doping and rGO inclusion, resulted in improved sensing parameters. CuFe₂O₄ nanoparticles prepared through sol-gel auto-combustion method, showed excellent sensitivity towards 25 ppm H₂S at 80 °C [22].

Among the various chemo-resistive metal oxides, cupric oxide (CuO) poses interesting properties like a p-type semiconducting nature, a narrow band gap (1.2 eV in bulk), high charge carrier concentrations, superior physical and chemical properties, ease of synthesis, versatile morphologies controlled through reaction conditions, reagent concentration and selectivity of synthetic method [23,24]. CuO nano/microstructures such as flower-shaped [25], nanoneedles [26], nanorods [27], nanowires [28], and nanosheets [29] have been synthesized utilizing hydrothermal, sol-gel, coprecipitation, electrospinning techniques. Owing to these versatile features, CuO nanostructures have been explored for numerous highly toxic volatile organic compounds and gases like ammonia [30], acetone [31], alcohols [32], liquified petroleum gas [33], carbon monoxide [34], sulphur dioxide [35], nitrogen dioxide [36] and many more. A detailed literature survey revealed that the two-dimensional CuO nanomaterials are rarely reported for the sensing of H₂S gas.

Herein, we are reporting a simple, economic and low temperature synthesis of leafshaped CuO nanosheets. As-synthesized CuO was examined through different techniques to confirm its formation, purity, crystal phase, morphology, vibrational, optical and diffraction features. A chemo-resistive type gas sensor based on leaf-shaped CuO nanosheets was fabricated to effectively and selectively detect H₂S gas. The sensor parameters were analyzed under varying degree of the operating temperatures and concentrations. Finally, a gas sensing mechanism was also proposed.

2. Materials and Methods

2.1. Synthesis of Leaf-Shaped CuO Nanosheets

Leaf-shaped CuO nanosheets were grown by a low temperature solution process. In a typical synthesis, 2 mmol of Copper (II) nitrate trihydrate (Cu(NO₃)₂·3H₂O) was first dissolved in 50 mL of deionized (DI) water under vigorous stirring for 1h. Separately 10 mmoL sodium hydroxide (NaOH) was freshly prepared in 20 mL DI water. Then NaOH solution was introduced to the Cu precursor solution under stirring until the pH of solution was reached to 11. Afterward, the reaction mixture was put into scotch Durant bottle and strongly tight the cover of the bottle. The Scotch Durant bottle was placed in an oven and maintained the temperature at 70 °C for 24 h. After completion of the reaction, the precipitate was washed several times with distilled water and ethanol repeatedly to remove the complexes and other impurities. Lastly, the desired product was dried at 80 °C to obtain CuO powder. Figure 1 depicts the typical schematic for the synthesis of leaf-shaped CuO nanosheets.



Figure 1. Schematic to synthesize leaf-shaped CuO nanosheets.

2.2. Characterization of Leaf-Shaped CuO Nanosheets

Field emission scanning electron microscopy (FESEM, JEOL-JSM-7600F, Boston, MA, USA) associated with energy dispersive spectroscopy (EDS) and transmission electron microscopy (TEM, JEOL-JEM-2100F; Boston, MA, USA) associated with high-resolution TEM (HRTEM) were utilized to examine the detailed structural, elemental, compositional, and morphological features of the hydrothermally synthesized leaf-shaped CuO nanosheets. X-ray diffractometer (XRD, PANanalytical Xpert Pro., Davis, CA, USA) studies were performed using Cu-K α radiation ($\lambda = 1.542$ Å) for analyzing the crystal phases and size for the synthesized CuO. Fourier transform infrared spectroscopic (FTIR, Perkin Elmer-FTIR Spectrum-100; Markham, ON, Canada) technique, through KBr palletization, along with Raman spectroscopy (Perkin Elmer-Raman Station-400 series, Markham, ON, Canada) were used to study the vibrational properties. The photoluminescence spectra (PL) were analyzed by the FP-6500 (JASCO, Easton, MD, USA) fluorometer using CuO suspension in ethanol solvent.

2.3. Fabrication of H₂S Gas Sensor Based on Leaf-Shaped CuO Nanosheets

A slurry was made, by mixing leaf-shaped CuO nanosheets with diethanolamine and ethanol, and coated on the surfaces of ceramic tube to obtain thick films. The gas sensing characteristics were examined by computer-controlled gas sensing analysis system. The details of the gas sensing system are presented elsewhere [16]. The test chamber volume is 4 L. During the sensing measurements, the heating system adjusts the temperature directly. When the resistance of the sensors became stable, the dynamic gas distribution system injected the target gas into the chamber. The sensors' resistance then changed, and the test chamber was opened when the resistance returned to normal, and the gas sensors would recover to origin states. The gas sensor response was defined as the ratio of device resistance in the presence of testing gas (R_g) and in air (R_a) at the same temperature (Equation (1)).

Gas response
$$=$$
 $\frac{R_g}{R_a}$ (1)

3. Results and Discussion

3.1. Characterizations

The surface features, morphology and microstructure of the as-synthesized CuO nanosheets were characterized by a field emission scanning electron microscope (FESEM) at resolution scales of 5 μ m (Figure 2a), 2 μ m (Figure 2b), 1 μ m (Figure 2c) and 500 nm (Figure 2d). All FESEM images revealed a thin leaf-like morphology for CuO nanosheets. The surfaces of the nanosheets were very smooth but the edges displayed small fringes, features similar to plant leaves. The average width of the leaf-shaped nanosheets was ~250 nm. However, the length-wise dimensions were quite variable.



Figure 2. (**a**,**b**) Low-magnification, (**c**,**d**) high-resolution FESEM images, (**e**) TEM image and (**f**) high-resolution TEM image of hydrothermally synthesized leaf-shaped CuO nanosheets.

More details of the microstructural properties of CuO nanoleaves were further explored through transmission electron microscopy (TEM; JEOL-JEM-2100F) equipped with high-resolution TEM (HRTEM). In Figure 2e,f the typical TEM and HRTEM images of a leaf-shaped CuO nano-sheet, respectively are shown. Thin leaf like morphologies of the CuO nanosheets, as examined through FESEM images, were confirmed by the TEM image

(Figure 2e). Similar to the reported literature, the interplanar distance of ~0.25 nm which corresponds to the (1 1 0) diffraction plane of the monoclinic phase of the CuO was from the HRTEM images (Figure 2f).

The crystalline phase of hydrothermally synthesized CuO leaf-shaped nanosheets was analyzed by XRD as shown in Figure 3. Well defined diffraction patterns at 20 values 32.45° , 35.45° , 38.65° , 46.25° , 48.75° , 53.50° , 58.25° , 61.50° , 66.25° and 68.00° are due to the lattice planes (110), ($\overline{1}11 - 002$), (111 - 002), ($11\overline{2}$), ($\overline{2}02$), (020), (202), ($\overline{1}13$), ($\overline{3}11$) and (220), respectively. These diffraction peaks and planes are the characteristics of the monoclinic tenorite crystalline phase of the CuO. The data is well-matched with the JCPDS 48–1548 card as well as the reported literature. Absence of peaks related to any other crystalline phase and impurity further indicate the successful synthesis of highly pure monophasic CuO nanoleaves via facile hydrothermal process.



Figure 3. XRD patterns of hydrothermally synthesized leaf-shaped CuO nanosheets.

The crystal size (d) of the leaf-shaped CuO with monoclinic crystalline phase was determined by using Debye-Scherrer equation (Equation (2)).

$$d = \frac{K\lambda}{\beta \cos\theta}$$
(2)

where K is a numerical factor (In this case K = 0.89), β is full width at half maximum (FWHM) and λ is 0.154 nm. Some of the most intense XRD peaks, as mentioned in Table 1 were used to calculate the FWHM. The average crystallite size for leaf-shaped CuO nanosheets was found to be 14.28 nm.

Diffraction Planes (hkl)	Diffraction Angles (°)	FWHM (β)	The Crystallite Size (nm)
(1 1 0)	32.45	0.7597	10.78
$(\overline{1} \ 1 \ 1 \ - 0 \ 0 \ 2)$	35.45	0.4275	19.31
(111-200)	38.65	0.5713	14.58
(202)	48.75	0.6051	14.26
(202)	58.25	0.7340	12.26
$(\overline{1} \ 1 \ 3)$	61.50	0.6320	14.48

Table 1. Diffraction parameters for leaf-shaped CuO nanosheets.

Since, for gas sensing applications, the composition and the purity of the gas sensor electrode material is of utmost importance, the as-synthesized leaf-shaped CuO nanosheets were subjected to elemental composition analysis using EDS attached with the FESEM. Figure 4a is representing the EDS spectrum of the leaf-shaped CuO nanosheets which shows only the spectral peaks for copper and oxygen elements. This ensured that the CuO nanosheets are free of any impurities.



Figure 4. (a) Typical EDS spectrum, (b) Raman spectrum, (c) FTIR spectrum and (d) Photoluminescence spectra of leaf-shaped CuO nanosheets.

Structural fingerprinting through Raman spectroscopy is an important qualitative technique to analyze the composition, vibrational and scattering properties of the metal oxide semiconductors [37]. The primitive cell for the monoclinic tenorite crystalline phase of CuO consists of two molecules per unit cell with the space group C_{2h}^6 [29]. In general, there are

nine zone-center optical phonon modes for CuO with symmetries $4A_u + 5B_u + A_g + 2B_g$. However, out of these modes only three phonon modes with symmetries A_g and $2B_g$ are Raman active [38]. The typical Raman spectrum for leaf-shaped CuO nanosheets consist of three distinct characteristic Raman peaks at 287, 344 and 620 cm⁻¹ (Figure 4b). The distinct sharp peak at 287 cm⁻¹ is attributed to A_g phonon mode, whereas less intense Raman peaks at 344 and 620 cm⁻¹ are assigned to B_g^1 and B_g^2 modes, respectively. The peaks are in good agreement with the Raman peaks reported for urchin like CuO hollow microspheres [39], CuO nanoplates [40] and CuO nanoparticles [41].

Figure 4c is representing the well-defined FTIR spectrum for the hydrothermally synthesized CuO nanosheets. FTIR peaks appeared at 523, 587, 1625 and 3427 cm⁻¹ for leaf-shaped CuO nanosheets. Very sharp vibrational peaks in the fingerprint region i.e., at 523 and 587 cm⁻¹ may be assigned to the stretching vibrations of the M-O bonds (In this case Cu-O bond) [42]. Additional peaks at 1625 cm⁻¹ and a wide FTIR band at 3427 cm⁻¹ may be attributed to the bending and stretching vibrations, respectively for the O–H groups of physiosorbed H₂O molecules on the surface of the leaf-shaped CuO nanosheets [43].

Photoluminescence (PL) spectroscopy is usually helpful in predicting the charge carrier trapping efficiencies, surface defects as well as the recombination of the e^-/h^+ pairs in a semiconductor metal oxide. PL spectrum of the leaf-shaped CuO nanosheets showed typical green emission within the wavelength range of 400–450 nm (Figure 4d). The broad nature of the PL spectrum further indicates the presence of the surface defects on CuO nanosheets [44]. Emission peaks at 414.4 and 431.8 nm are supposed to arises from the ionized oxygen vacancies resulting in green emission from the surface of the leaf-shaped CuO nanosheets [45]. The band gap for CuO was calculated from the emission peaks at 414.4 and 431.8 nm using well-known Planck's equation (Equation (3)). The calculated band gap was in the range 2.99–2.87 eV which is close to the reported value [45].

$$E_{g} = \frac{hc}{\lambda_{max}}$$
(3)

3.2. H₂S Gas Sensing Applications of CuO Nanosheets

Semiconductor metal oxides are the key component of the most of the recently studied gas sensors due to their low-cost synthesis, biocompatibility, ease of sensor fabrication and excellent gas sensing behavior. Gas sensing parameters of such sensors are controlled by different factors like operating temperature, gas concentration, composition of the sensor material, surface modifications, crystal size, and most importantly the nature of the gas which significantly contributes to the selectivity of the sensor.

One of the most important controlling factors is the operating temperature since it controls the adsorption \rightleftharpoons desorption equilibrium of the gas and O₂ molecules, kinetics of the redox reactions, and concentration of oxygen vacancies on the surface of the sensor materials. Herein, the optimized temperature was found to be 300 °C for the sensing of 200 ppm H₂S gas through leaf-shaped CuO nanosheets based gas sensor device. The corresponding gas response was 35.3 at optimized temperature. Low sensor response below 300 °C is due to insufficiently activation of the H₂S gas molecules to react with the surface adsorbed O₂ molecules (Figure 5a). As the temperature is increased more O₂ molecules, thereby increasing gas response. However, beyond optimized temperature, the increased rate of the desorption of the H₂S and O₂ molecules decreases the gas response.



Figure 5. (a) Gas sensor response to 200 ppm H_2S gas as a function of the operating temperature, (b,c) dependency of gas sensor response on low and high concentration, respectively for H_2S gas at optimized temperature and (d) Dynamic response plots for leaf-shaped CuO nanosheets based H_2S gas sensor.

The gas sensor response depends upon the rate of the redox reactions occurring at the surface of the sensor material, which in turn is directly proportional to the concentration of the analyte gas. Therefore, the gas responses of the leaf-shaped CuO nanosheets based gas sensor for low concentrations (10–100 ppm) (Figure 5b) as well as high concentrations (100–450 ppm) (Figure 5c) of the H₂S gas, at an optimized temperature of 300 °C, were recorded. Excellent linearities were observed between the gas response and H₂S concentration with determinant coefficients of 0.99545 and 0.99710 for low and high concentration ranges, respectively. The real time dynamic response-recovery curves for the fabricated sensor against different concentrations of the H₂S gas ranging from 50–250 ppm at 300 °C are shown in Figure 5d. The gas response steeply increased in the presence of the analyte gas and as soon as the supply of the gas was interrupted, the gas response returned to the original baseline value. The behavior was observed for all the chosen H₂S concentrations at optimum temperature. Excellent gas response can be attributed to the unique nanosheet like morphology for of CuO which provide a large specific surface area for the high extent of adsorption of O₂ and H₂S gas molecules.

The repeatability and reusability aspects of the CuO nanosheets based sensor towards sequential exposure of 200 ppm H_2S gas at optimized temperature of 300 °C were examined by analyzing gas responses for successive twelve cycles. The outcomes of the analysis are shown in Figure 6a. Perfectly matched gas responses for each cycle indicate excellent response reproducibility of the fabricated H_2S gas sensors. The response and recovery

times are also two important factors in the gas sensor applications. The response (τ_{res}) and recovery time (τ_{rec}) relate to the time required by the sensor to attain the 90% steady response value and the time required to reach 10% of the initial gas response, respectively [35]. Figure 6b shows the response and recovery curves for leaf-shaped CuO nanosheets based gas sensor towards 200 ppm of H₂S gas at optimized temperature. Response and recovery times were 97 s and 100 s, respectively.



Figure 6. (a) Reproducibility study and (b) Response curve for the calculation of response and recovery times.

Inspired by the excellent gas sensing behavior of the as-fabricated gas sensor, the selectivity test was also performed (Figure 7). The test shows that the leaf-shaped CuO nanosheets based gas sensor was more selective towards H_2S gas as compared to other analyte gases including NH₃, CH₃OH, CH₃CH₂OH, CO and H₂. For 200 ppm concentrations, the gas responses towards H_2S observed were 4.84, 3.21, 2.94, 5.19 and 6.30 times higher than NH₃, CH₃OH, CH₃CH₂OH, CO and H₂, respectively at 300 °C temperature.



Figure 7. Selectivity studies of the leaf-shaped CuO nanosheets based H₂S gas sensor.

3.3. Proposed Gas Sensing Mechanism

Since CuO is a typical p-type semiconductor metal oxide, its gas-sensing behavior is attributed to the change in the resistance resulted due to redox reactions occurring on its surface between the H₂S gas molecules and various oxygenated anionic species. The resistance changes are also resulted by the adsorption \Rightarrow desorption equilibrium of the analyte gases as a function of temperature and the concentration. In the presence of air ambient conditions, p-type CuO semiconductor ionizes adsorbed O₂ molecules into various anionic species including O_2^- , O_2^{2-} , O^{2-} and O^- at optimized temperature conditions utilizing the conduction band electrons (Equations (4)–(6)). This loss of electrons from the conduction band forms a positively charged hole accumulation layer.

$$O_{2(g)} \rightarrow O_{2(ads)}$$
 (4)

$$O_{2(g)} \stackrel{e_{CB}^-}{\to} O_{2(ads)}^- \stackrel{e_{CB}^-}{\to} O_{2(ads)}^{2-}$$
(5)

$$O_{2(g)} \xrightarrow{e_{CB}^{-}} 2O_{(ads)}^{-} \xrightarrow{e_{CB}^{-}} 2O_{(ads)}^{2-}$$
(6)

Due to the formation of positively charged hole accumulation layer near the surface of the CuO nanosheets which stimulates a competitive resistance between the highly insulating resistive core and the hole accumulation layer [29].

The oxidation of the H_2S to SO_2 and H_2O on the surface of the leaf-shaped CuO nanosheet results in the release of the electrons which are trapped by the positively charged holes resulting in electron-hole recombination (Equations (7)–(9)). The thickness of the hole depletion layer is decreased which subsequently enhances the resistance of the leaf-shaped CuO nanosheets [46] (Figure 8).

$$H_2S + 3O^-_{(Adsorbed)} \to SO_2 + H_2O + 3e^-$$
 (7)

$$H_2S + 3 O^{2-}_{(Adsorbed)} \to SO_2 + H_2O + 6 e^-$$
 (8)

$$e^- + h^+ \rightarrow Null$$
 (9)



Figure 8. Schematics of the H₂S gas sensing mechanism by leaf-shaped CuO nanosheets.

In order to further justify the novelty of the present work, a comparative analysis of the gas sensor parameters of the present study is shown in Table 2 and compared to other reported CuO nanostructures. From the Table 2, it can be inferred that as-synthesized leaf-shaped CuO nanosheets show the better gas sensing performance as compared to reported pure CuO nanostructures and composites of CuO.

Sensor Material	Conc.	Gas Response	Response Time (s)	Recovery Time (s)	T (°C)	Ref.
CuO nanosheets	2 ppb	320 *	4	9	240	[47]
Porous CuO nanosheet	10 ppb	1.25 #	234	76	RT	[48]
rGO/CuO nanofibers	10 ppm	11.7 \$	-	-	300	[49]
Hierarchically flower-like CuO	1 ppm	2.1 ^{\$}	240	1341	RT	[50]
CuO-ZnO hollow spheres	5 ppm	13.3 #	270	720	336	[51]
Hierarchical CuO/NiO nanowall arrays	5 ppm	36.9 \$	-	13	133	[52]
CuO/MoS ₂ film	30 ppm	61 *	26	11	RT	[53]
CuO nanosheet monolayer	200	350 *	20	120	250	[54]
Leaf-shaped CuO nanosheets	200	35.3 \$	97	100	300	This work

Table 2. Sensing parameters for various CuO gas sensor materials towards H₂S gas.

* Gas response = $\frac{(R_g - R_a)100}{R_a}$, # Gas response = $\frac{R_a}{R_g}$, \$ Gas response = $\frac{R_g}{R_a}$.

4. Conclusions

In summary, leaf-shaped CuO nanosheets were prepared through facile low temperature hydrothermal process and were subsequently characterized. The average width of the leaf-shaped nanosheets was ~250 nm and the surface were smooth but the edges displayed small fringes. The H_2S gas sensor was fabricated using as-synthesized leaf-shaped CuO nanosheets. At the optimized temperature conditions, a gas response of 35.3 was observed for 200 ppm H_2S gas. Outstanding linearity between gas response and the concentrations of the H_2S gas were shown at low as well as high concentration ranges. Additionally, the fabricated sensors also showed good repeatability and selectivity. The excellent gas response for leaf-shaped CuO nanosheets gas sensors are due to the unique nanosheet-like morphology for of CuO which provide a large specific surface area for the high extent of adsorption of O_2 and H_2S gas molecules. From these findings, it can be presumed that gas sensors based on leaf-shaped CuO nanosheets may, in near future, be suitable materials for the detection of highly toxic gases like H₂S.

Author Contributions: Author Contributions: Conceptualization, A.U., H.A. (Hassan Algadi), M.S.A., A.A.I. and W.Z.; methodology, A.U., H.A. (Hassan Algadi), M.S.A., A.A.I., H.A. (Hasan Albargi) and W.Z.; software, A.U., H.A. (Hassan Algadi), R.K., M.S.A., A.A.I., H.A. (Hasan Albargi), and M.A.M.A.; formal analysis, A.U., H.A.(Hassan Algadi), R.K., M.S.A., A.A.I., H.A. (Hasan Albargi), M.A.M.A., T.A. and W.Z.; investigation, A.U., H.A. (Hassan Algadi), R.K., M.S.A., A.A.I., H.A. (Hasan Albargi), M.A.M.A., T.A. and W.Z.; investigation, A.U., H.A. (Hassan Algadi), R.K., M.S.A., A.A.I., H.A. (Hasan Albargi), M.A.M.A., T.A. and W.Z. writing— original draft preparation, A.U. R.K., M.S.A.; writing—review and editing, A.U., R.K., M.S.A. and W.Z. All authors have read and agreed to the published version of the manuscript.

Funding: This research was funded by the Deputy for Research and Innovation-Ministry of Education, Kingdom of Saudi Arabia through a grant (NU/IFC/INT/01/004) under the institutional funding committee at Najran University, Kingdom of Saudi Arabia.

Institutional Review Board Statement: Not applicable.

Informed Consent Statement: Not applicable.

Data Availability Statement: Data is contained within the article.

Acknowledgments: Authors would like to acknowledge the support of the Deputy for Research and Innovation-Ministry of Education, Kingdom of Saudi Arabia for the research through a grant (NU/IFC/INT/01/004) under the institutional funding committee at Najran University, Kingdom of Saudi Arabia.

Conflicts of Interest: The authors declare no conflict of interest.

References

- 1. Umar, A.; Alduraibi, M.; Al-Dossary, O. NOx Gas Sensing Properties of Fe-Doped ZnO Nanoparticles. *Sci. Adv. Mater.* **2020**, *12*, 908–914. [CrossRef]
- Sampaolo, A.; Yu, C.; Wei, T.; Zifarelli, A.; Giglio, M.; Patimisco, P.; Zhu, H.; Zhu, H.; He, L.; Wu, H.; et al. H₂S quartz-enhanced photoacoustic spectroscopy sensor employing a liquid-nitrogen-cooled THz quantum cascade laser operating in pulsed mode. *Photoacoustics* 2021, 21, 100219. [CrossRef]
- Wu, C.; Ye, G.; Qi, L.; Wang, Y.; Yuan, C.; Zhang, L. Novel ZnO Sensor and Gas Detection Performance in Tunnel Construction. J. Nanoelectron. Optoelectron. 2020, 15, 1114–1119. [CrossRef]
- 4. Zhu, M.; Zhang, L. A Novel H 2 S Gas Sensor Applied to the Construction Workers During the Construction Process. *Sci. Adv. Mater.* **2018**, *11*, 143–146. [CrossRef]
- Zhang, S.; Liu, Z.; Zhang, L.; Chen, J.; Zhou, Q.; Zhang, H.; Nie, L.; Dong, Z.; Zhang, Z.; Wang, Z.; et al. Construction of a low-temperature, highly sensitive H₂S sensor based on surfaces and interfaces reaction triggered by Au-doped hierarchical structured composites. *Chem. Phys. Lett.* 2021, 763, 138188. [CrossRef]
- Wu, C.; Yuan, C.; Qi, L.; Wang, Y.; Guo, Y. A Novel Hydrogen Sulfide Gas Sensor Apply in Tunnel Construction. *Sci. Adv. Mater.* 2018, 11, 112–115. [CrossRef]
- Li, Z.-Y.; Wu, G.; Chen, J.-Y.; Li, W.-C. A Novel Gas Sensor Detection of Hydrogen Sulfide in Tunnel Construction. *Sci. Adv. Mater.* 2018, 11, 147–151. [CrossRef]
- Pravarthana, D.; Tyagi, A.; Jagadale, T.C.; Prellier, W.; Aswal, D.K. Highly sensitive and selective H2S gas sensor based on TiO2 thin films. *Appl. Surf. Sci.* 2021, 549, 149281. [CrossRef]
- 9. Cho, M.; Eom, T.; Nundy, S.; Park, J.-S.; Lee, H.-J. Conductometric nitrogen dioxide gas sensors based on sol-gel-prepared hafnium-added indium zinc oxide (Hf-IZO). *Sens. Actuators B Chem.* **2021**, *344*, 130198. [CrossRef]
- Pi, M.; Zheng, C.; Bi, R.; Zhao, H.; Liang, L.; Zhang, Y.; Wang, Y.; Tittel, F.K. Design of a mid-infrared suspended chalcogenide/silica-on-silicon slot-waveguide spectroscopic gas sensor with enhanced light-gas interaction effect. *Sens. Actuators B Chem.* 2019, 297, 126732. [CrossRef]
- 11. Bao, Y.; Xu, P.; Cai, S.; Yu, H.; Li, X. Detection of volatile-organic-compounds (VOCs) in solution using cantilever-based gas sensors. *Talanta* **2018**, *182*, 148–155. [CrossRef]
- 12. Lee, J.H.; Park, M.S.; Jung, H.; Choe, Y.-S.; Kim, W.; Song, Y.G.; Kang, C.-Y.; Lee, H.-S.; Lee, W. Selective C₂H₂ detection with high sensitivity using SnO₂ nanorod based gas sensors integrated with a gas chromatography. *Sens. Actuators B Chem.* **2020**, 307, 127598. [CrossRef]
- Maurya, J.B.; Prajapati, Y.K.; Raikwar, S.; Saini, J.P. A silicon-black phosphorous based surface plasmon resonance sensor for the detection of NO₂ gas. *Optik* 2018, 160, 428–433. [CrossRef]
- 14. Grabka, M.; Jasek, K.; Pasternak, M. Application of polymethyl [4-(2,3-difluoro-4-hydroxyphenoxy) butyl] siloxane in surface acoustic wave gas sensors for dimethyl methylphosphonate detection. *Sens. Actuators B Chem.* **2021**, 329, 129216. [CrossRef]

- 15. Zhang, P.; Xiao, Y.; Zhang, J.; Liu, B.; Ma, X.; Wang, Y. Highly sensitive gas sensing platforms based on field effect Transistor-A review. *Anal. Chim. Acta* 2021, 1172, 338575. [CrossRef] [PubMed]
- 16. Zhong, Z.-C.; Han, X.; Liu, K.-Y.; Xu, Y.; Lin, J. Rapid and Sensitive Acetylene Gas Sensor Based on TiO 2 Nanoparticles. *Sci. Adv. Mater.* **2019**, *11*, 1126–1132. [CrossRef]
- 17. Zhou, M.; Chen, X.; Zhang, L.; Zeng, W. High Performance Novel Gas Sensor Device for Site Environmental Protection Using Ti 0.5 Sn 0.5 O 2 Nanomaterials. *J. Nanoelectron. Optoelectron.* **2021**, *15*, 1423–1428. [CrossRef]
- 18. Shaik, M.; Rao, V.K.; Gupta, M.; Murthy, K.S.R.C.; Jain, R. Chemiresistive gas sensor for the sensitive detection of nitrogen dioxide based on nitrogen doped graphene nanosheets. *RSC Adv.* **2016**, *6*, 1527–1534. [CrossRef]
- 19. Qiao, X.; Xu, Y.; Yang, K.; Ma, J.; Li, C.; Wang, H.; Jia, L. Mo doped BiVO₄ gas sensor with high sensitivity and selectivity towards H₂S. *Chem. Eng. J.* **2020**, *395*, 125144. [CrossRef]
- Li, S.; Xie, L.; He, M.; Hu, X.; Luo, G.; Chen, C.; Zhu, Z. Metal-Organic frameworks-derived bamboo-like CuO/In₂O₃ Heterostructure for high-performance H₂S gas sensor with Low operating temperature. *Sens. Actuators B Chem.* 2020, 310, 127828. [CrossRef]
- 21. Hosseini, Z.S.; Iraji zad, A.; Mortezaali, A. Room temperature H₂S gas sensor based on rather aligned ZnO nanorods with flower-like structures. *Sens. Actuators B Chem.* **2015**, 207, 865–871. [CrossRef]
- Shewale, P.S.; Yun, K.-S. Synthesis and characterization of Cu-doped ZnO/RGO nanocomposites for room-temperature H2S gas sensor. J. Alloy. Compd. 2020, 837, 155527. [CrossRef]
- Haija, M.A.; Abu-Hani, A.F.S.; Hamdan, N.; Stephen, S.; Ayesh, A.I. Characterization of H2S gas sensor based on CuFe2O4 nanoparticles. J. Alloy. Compd. 2017, 690, 461–468. [CrossRef]
- 24. Ighalo, J.O.; Sagboye, P.A.; Umenweke, G.; Ajala, O.J.; Omoarukhe, F.O.; Adeyanju, C.A.; Ogunniyi, S.; Adeniyi, A.G. CuO nanoparticles (CuO NPs) for water treatment: A review of recent advances. *Environ. Nanotechnol. Monit. Manag.* **2021**, *15*, 100443. [CrossRef]
- 25. Zhu, W.; An, X.; Huangfu, W.; Chi, J.; Xu, L. A Novel CuO flower like nanomaterials and its fault detection performance in power cable. *J. Nanoelectron. Optoelectron.* **2020**, *15*, 1146–1150.
- 26. Yang, C.; Xiao, F.; Wang, J.; Su, X. 3D flower- and 2D sheet-like CuO nanostructures: Microwave-assisted synthesis and application in gas sensors. *Sens. Actuators B Chem.* 2015, 207, 177–185. [CrossRef]
- 27. Hu, Q.; Zhang, W.; Wang, X.; Wang, Q.; Huang, B.; Li, Y.; Hua, X.; Liu, G.; Li, B.; Zhou, J.; et al. Binder-free CuO nanoneedle arrays based tube-type sensor for H₂S gas sensing. *Sens. Actuators B Chem.* **2021**, *326*, 128993. [CrossRef]
- 28. Yang, C.; Su, X.; Xiao, F.; Jian, J.; Wang, J. Gas sensing properties of CuO nanorods synthesized by a microwave-assisted hydrothermal method. *Sens. Actuators B Chem.* **2011**, *158*, 299–303. [CrossRef]
- 29. Kim, J.H.; Katoch, A.; Choi, S.W.; Kim, S.S. Growth and sensing properties of networked p-CuO nanowires. *Sens. Actuators B Chem.* 2015, 212, 190–195. [CrossRef]
- 30. Umar, A.; Alshahrani, A.A.; Algarni, H.; Kumar, R. CuO nanosheets as potential scaffolds for gas sensing applications. *Sens. Actuators B Chem.* **2017**, 250, 24–31. [CrossRef]
- 31. Chaloeipote, G.; Prathumwan, R.; Subannajui, K.; Wisitsoraat, A.; Wongchoosuk, C. 3D printed CuO semiconducting gas sensor for ammonia detection at room temperature. *Mater. Sci. Semicond. Process.* **2021**, *123*, 105546. [CrossRef]
- 32. Rezaei, K.; Nasirian, S. A low-level acetone gas sensor based on n-type ZnO/p-type CuO composite nanostructure for the diagnosis of diabetes in dynamic situations. *J. Mater. Sci. Mater. Electron.* **2021**, *32*, 5199–5214. [CrossRef]
- 33. Wang, F.; Li, H.; Yuan, Z.; Sun, Y.; Chang, F.; Deng, H.; Xie, L.; Li, H. A highly sensitive gas sensor based on CuO nanoparticles synthetized via a sol–gel method. *RSC Adv.* **2016**, *6*, 79343–79349. [CrossRef]
- 34. Singh, S.; Verma, N.; Singh, A.; Yadav, B.C. Synthesis and characterization of CuO–SnO₂ nanocomposite and its application as liquefied petroleum gas sensor. *Mater. Sci. Semicond. Process.* **2014**, *18*, 88–96. [CrossRef]
- 35. Liao, L.; Zhang, Z.; Yan, B.; Zheng, Z.; Bao, Q.L.; Wu, T.; Li, C.M.; Shen, Z.X.; Zhang, J.X.; Gong, H.; et al. Multifunctional CuO nanowire devices: P-type field effect transistors and CO gas sensors. *Nanotechnology* **2009**, *20*, 085203. [CrossRef] [PubMed]
- Bai, B.C.; Lee, C.W.; Lee, Y.-S.; Im, J.S. Modification of textural properties of CuO-supported activated carbon fibers for SO₂ adsorption based on electrical investigation. *Mater. Chem. Phys.* 2017, 200, 361–367. [CrossRef]
- 37. Li, Z.; Liu, Y.; Guo, D.; Guo, J.; Su, Y. Room-temperature synthesis of CuO/reduced graphene oxide nanohybrids for highperformance NO2 gas sensor. *Sens. Actuators B Chem.* **2018**, 271, 306–310. [CrossRef]
- Cunniff, C.Z.; Specht, S.E.; Love, A.M.; Uchupalanun, P.; Venegas, J.M.; Kruszynski, C.E.; Hermans, I. Investigation of supported metal oxide species with shell-isolated nanoparticle-enhanced Raman spectroscopy. J. Phys. Chem. C 2019, 123, 25220–25227. [CrossRef]
- 39. Debbichi, L.; Marco de Lucas, M.C.; Pierson, J.F.; Krüger, P. Vibrational Properties of CuO and Cu₄O₃ from First-Principles Calculations, and Raman and Infrared Spectroscopy. *J. Phys. Chem. C* 2012, *116*, 10232–10237. [CrossRef]
- 40. Umar, A.; Ibrahim, A.A.; Ammar, H.Y.; Nakate, U.T.; Albargi, H.B.; Hahn, Y.B. Urchin like CuO hollow microspheres for selective high response ethanol sensor application: Experimental and theoretical studies. *Ceram. Int.* **2021**, *47*, 12084–12095. [CrossRef]
- Umar, A.; Ibrahim, A.A.; Nakate, U.T.; Albargi, H.; Alsaiari, M.A.; Ahmed, F.; Alharthi, F.A.; Ali Alghamdi, A.; Al-Zaqri, N. Fabrication and characterization of CuO nanoplates based sensor device for ethanol gas sensing application. *Chem. Phys. Lett.* 2021, 763, 138204. [CrossRef]

- 42. Rashad, M.; Rüsing, M.; Berth, G.; Lischka, K.; Pawlis, A. CuO and Co₃O₄ nanoparticles: Synthesis, characterizations, and raman spectroscopy. *J. Nanomater.* **2013**, 2013, 714853. [CrossRef]
- Veisi, H.; Karmakar, B.; Tamoradi, T.; Hemmati, S.; Hekmati, M.; Hamelian, M. Biosynthesis of CuO nanoparticles using aqueous extract of herbal tea (Stachys Lavandulifolia) flowers and evaluation of its catalytic activity. *Sci. Rep.* 2021, *11*, 1983. [CrossRef] [PubMed]
- 44. Jadhav, M.S.; Kulkarni, S.; Raikar, P.; Barretto, D.A.; Vootla, S.K.; Raikar, U.S. Green biosynthesis of CuO & Ag–CuO nanoparticles from Malus domestica leaf extract and evaluation of antibacterial, antioxidant and DNA cleavage activities. *New J. Chem.* **2018**, 42, 204–213. [CrossRef]
- 45. Huang, C.-Y.; Chatterjee, A.; Liu, S.B.; Wu, S.Y.; Cheng, C.-L. Photoluminescence properties of a single tapered CuO nanowire. *Appl. Surf. Sci.* **2010**, *256*, 3688–3692. [CrossRef]
- 46. Sagadevan, S.; Pal, K.; Chowdhury, Z.Z. Fabrication of CuO nanoparticles for structural, optical and dielectric analysis using chemical precipitation method. *J. Mater. Sci. Mater. Electron.* **2017**, *28*, 12591–12597. [CrossRef]
- 47. Lupan, O.; Postica, V.; Cretu, V.; Wolff, N.; Duppel, V.; Kienle, L.; Adelung, R. Single and networked CuO nanowires for highly sensitive p-type semiconductor gas sensor applications. *Phys. Status Solidi Rapid Res. Lett.* **2016**, *10*, 260–266. [CrossRef]
- Zhang, F.; Zhu, A.; Luo, Y.; Tian, Y.; Yang, J.; Qin, Y. CuO nanosheets for sensitive and selective determination of H₂S with high recovery ability. J. Phys. Chem. C 2010, 114, 19214–19219. [CrossRef]
- 49. Li, Z.; Wang, N.; Lin, Z.; Wang, J.; Liu, W.; Sun, K.; Fu, Y.Q.; Wang, Z. Room-temperature high performance H₂S sensor based on porous CuO nanosheets prepared by hydrothermal method. *ACS Appl. Mater. Interfaces* **2016**, *8*, 20962–20968. [CrossRef]
- 50. Kim, J.-H.; Mirzaei, A.; Zheng, Y.; Lee, J.-H.; Kim, J.-Y.; Kim, H.W.; Kim, S.S. Enhancement of H₂S sensing performance of p-CuO nanofibers by loading p-reduced graphene oxide nanosheets. *Sens. Actuators B Chem.* **2019**, *281*, 453–461. [CrossRef]
- 51. Li, Z.; Wang, J.; Wang, N.; Yan, S.; Liu, W.; Fu, Y.Q.; Wang, Z. Hydrothermal synthesis of hierarchically flower-like CuO nanostructures with porous nanosheets for excellent H₂S sensing. *J. Alloy. Compd.* **2017**, 725, 1136–1143. [CrossRef]
- 52. Kim, S.-J.; Na, C.W.; Hwang, I.-S.; Lee, J.-H. One-pot hydrothermal synthesis of CuO–ZnO composite hollow spheres for selective H₂S detection. *Sens. Actuators B Chem.* **2012**, *168*, 83–89. [CrossRef]
- Sui, L.; Yu, T.; Zhao, D.; Cheng, X.; Zhang, X.; Wang, P.; Xu, Y.; Gao, S.; Zhao, H.; Gao, Y.; et al. In Situ deposited hierarchical CuO/NiO nanowall arrays film sensor with enhanced gas sensing performance to H₂S. *J. Hazard. Mater.* 2020, 385, 121570. [CrossRef] [PubMed]
- 54. Zhang, D.; Wu, J.; Cao, Y. Ultrasensitive H₂S gas detection at room temperature based on copper oxide/molybdenum disulfide nanocomposite with synergistic effect. *Sens. Actuators B Chem.* **2019**, *287*, 346–355. [CrossRef]